NC/QC/BD/2020-21/RS-C1

Date: 02-05-2020

1. TEST REPORT ON CEMENT:

Sub: Testing of 53 Grade Cement Sample (IS 12269-1987).
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

PHYSICAL TESTS ON CEMENT

Grade * : 53,
Type * : O.P.C

TABLE 1.1:

SL No	Name of Test	Test Results	Requirements as per IS 8112-1989
1	Initial setting time	**154 min**	Shall not be less than 30 min
2	Final setting time	**265 min**	Shall not be more than 600 min
3	Fineness (by dry sieving on IS 90 micron sieve)	**2.13%**	Not to exceed 10.0%
4	Soundness test(by Le-Chatelier's method)	**2.08mm**	Shall not be more than 10 mm
5	Compressive strength a) 3 days (average of three results)	**28.65 N/Sq mm**	Shall not be less than 27 N/Sqmm

For Newzen Consultants Bangalore
Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned with CamScanner

NC/QC/BD/2020-21/RS-PCC1 **Date: 02-05-2020**

1. TESTING OF COARSE AND FINE AGGREGATES:

Sub: Testing of Coarse and Fine aggregates to be used for bed concrete.
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

1. COARSE AGGRGATES TABLE - SIEVE ANALYSIS:

IS Sieve Size, mm	Percentage passing	Requirements as per IS 383-1970 (Reaffirmed on 2007) % Passing	
	40 mm Sample	Single size	Graded
40mm	100.00	85-100	90 – 100
20mm	67.45	0 -20	30- 70
10mm	31.25	0 -5	10- 35
4.75mm	3.75	------	0- 5

2. FINE AGGREGATES TABLE - SIEVE ANALYSIS:

IS Sieve Size, mm	Percentage Passing	Specification as Per IS: 383-1970(Reaffirmed 2002) Percentage Passing			Remarks
		Zone-I	Zone-II	Zone -III	
04.75	96.50	90-100	90-100	90-100	The Sample Conforms to Grading Zone-II
02.36	82.35	60-95	75-100	85-100	
01.18	74.15	30-70	55-90	75-100	
600.mic	47.25	15-34	35-59	60-79	
300.mic	23.80	5-20	8-30	12-40	
150.mic	7.65	0-10	0-10	0-10	

Page No. 1/1,

For Newzen Consultants Bangalore
Proprietor

Scanned with CamScanner

NC/QC/BD/2020-21/RS-C2 **Date: 04-05-2020**

1. TEST REPORT ON CEMENT:

Sub: Testing of 53 Grade Cement Sample (IS 12269-1987).
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

PHYSICAL TESTS ON CEMENT

Grade * : 53,
Type * : O.P.C

TABLE 1.1:

SL No	Name of Test	Test Results	Requirements as per IS 8112-1989
1	Initial setting time	**156 min**	Shall not be less than 30 min
2	Final setting time	**265 min**	Shall not be more than 600 min
3	Fineness (by dry sieving on IS 90 micron sieve)	**2.15 %**	Not to exceed 10.0%
4	Soundness test(by Le-Chatelier's method)	**2.03 mm**	Shall not be more than 10 mm
5	Compressive strength b) 3 days (average of three results)	**29.06 N/Sq mm**	Shall not be less than 27 N/Sqmm

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned with CamScanner

NC/QC/BD/2020-21/RS-PCC2 **Date: 04-05-2020**

1. TESTING OF COARSE AND FINE AGGREGATES:

Sub: Testing of Coarse and Fine aggregates to be used for bed concrete.
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

1. COARSE AGGRGATES TABLE - SIEVE ANALYSIS:

IS Sieve Size, mm	Percentage passing	Requirements as per IS 383-1970 (Reaffirmed on 2007) % Passing	
	40 mm Sample	Single size	Graded
40mm	**100.00**	85-100	90 – 100
20mm	**63.45**	0 -20	30- 70
10mm	**29.65**	0 -5	10- 35
4.75mm	**4.15**	------	0- 5

2. FINE AGGREGATES TABLE - SIEVE ANALYSIS:

IS Sieve Size, mm	Percentage Passing	Specification as Per IS: 383-1970(Reaffirmed 2002) Percentage Passing			Remarks
		Zone-I	Zone-II	Zone -III	
04.75	**97.25**	90-100	90-100	90-100	The Sample Conforms to Grading **Zone-II**
02.36	**83.15**	60-95	75-100	85-100	
01.18	**71.50**	30-70	55-90	75-100	
600.mic	**45.85**	15-34	35-59	60-79	
300.mic	**23.10**	5-20	8-30	12-40	
150.mic	**6.90**	0-10	0-10	0-10	

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

Page No. 1/1,

For Newzen Consultants Bangalore
Proprietor

Scanned with CamScanner

NC/QC/BD/2020-21/RS-C3 **Date: 06-05-2020**

1. TEST REPORT ON CEMENT:

Sub: Testing of 53 Grade Cement Sample (IS 12269-1987).
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

PHYSICAL TESTS ON CEMENT

Grade * : 53,
Type * : O.P.C

TABLE 1.1:

SL No	Name of Test	Test Results	Requirements as per IS 8112-1989
1	Initial setting time	**152 min**	Shall not be less than 30 min
2	Final setting time	**275 min**	Shall not be more than 600 min
3	Fineness (by dry sieving on IS 90 micron sieve)	**1.85 %**	Not to exceed 10.0%
4	Soundness test(by Le-Chatelier's method)	**1.98 mm**	Shall not be more than 10 mm
5	Compressive strength a) 3 days (average of three results)	**28.54 N/Sq mm**	Shall not be less than 27 N/Sqmm

Page No. 1/1,

For, Newzen Consultants Bangalore
Proprietor

Scanned with CamScanner

NC/QC/BD/2020-21/RS-FA1 **Date: 06-05-2020**

1. TESTING OF FINE AGGREGATES :

Sub. Testing of Fine Aggregates.
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

TABLE - 1.1 : SIEVE ANALYSIS :

IS Sieve Size,mm	Percentage Passing	Specification as Per IS: 383-1970(Reaffirmed 2002) Percentage Passing			Remarks
		Zone-I	Zone-II	Zone -II	
04.75	**96.25**	90-100	90-100	90-100	The Sample Conforms to Grading **Zone-II**
02.36	**83.40**	60-95	75-100	85-100	
01.18	**71.10**	30-70	55-90	75-100	
600. mic	**46.35**	15.34	35-59	60-79	
300.mic	**22.90**	5-20	8-30	12-40	
150.mic	**7.55**	0-10	0-10	0-10	

TABLE 1.2 ;

Sl No	Test Conducted	Sample	Results	Requirements as Per IS. Specification IS :383-1970 (Reaffirmed 2002)
1	Bulking of Sand	001	**17.65%**	-----
2	Silt Content	----	**0.58%**	Not more than 8%
3	Specific Gravity	----	**2.61**	-------

Page No. 1/1,

For Newzen Consultants Bangalore

Scanned with CamScanner

NC/QC/BD/2020-21/RS-CA1 **Date: 06-05-2020**

1. TESTING OF COARSE AGGREGATES (20 mm):

Sub: Testing of Construction Materials.
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

Table - 1.1 : SIEVE ANALYSIS :

IS Sieve Size, mm	Percentage passing	Requirements as per IS 383-1970 (Reaffirmed on 2002) % Passing	
	20 mm Sample	Single size	Graded
40 mm	100.00	100.00	100.00
20 mm	97.25	85-100	90 - 100
10 mm	45.10	0 - 20	25 - 55
4.75 mm	3.70	0 - 5	0 - 10

TABLE 1.2 :

SL No	Test conducted	Results	Requirements as per IS:383-1970 & Tests Conforms to IS 2386(Part I to IV) – 1963 (Reaffirmed on 2002)
1.	Flakiness Index	26.49%	Not to exceed 25 %
2.	Crushing value	28.72 %	Not to exceed 45 % for concrete other than for wearing surfaces and 30% for concrete for wearing surfaces

For Newzen Consultants Bangalore
Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned with CamScanner

NC/QC/BD/2020-21/RS-S1 Date: 06-05-2020

1. TEST REPORT ON REINFORCEMENT STEEL:

Sub: Testing of Reinforcement Steel of diameter 10 and 12 mm **TMT Steel.**
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

TABLE – 1

SL No	Details	For 10 mm		For 12 mm	
		Test Results	Min Req. as per IS 1786-2008	**Test Results**	Min Req. as per IS 1786-2008
01	Observed diameter of bar	**10.0 mm**	10.0 mm	**12.0 mm**	12.0 mm
02	Observed Wt/m Length **Kg/m**	**0.620**	0.567	**0.891**	0.834
03	Proof stress/Yield stress, fy , **N/mm^2**	**554.0**	500.0	**558.0**	500.0
04	Bend/ Re bend Test	**Ok**	---	**Ok**	---
05	Percentage of Elongation, %	**20.50**	16.00	**19.80**	16.00
06	Ultimate Tensile Strength **N/mm^2**	**645.0**	565.0	**649.0**	565.0

Page No. 1/1,

For Newzen Consultants Bangalore
Proprietor

Scanned with CamScanner

NC/QC/BD/2020-21/RS-CB1 Date: 14-05-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K N	Compressive Strength (N/mm^2)	Avg. Value
1	001	07-05-20	14-05-20	07	22500	360	16.00	16.07
	002	"	"	"	"	355	15.78	
	003	"	"	"	"	370	16.44	

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned with CamScanner

NC/QC/BD/2020-21/RS-CB2 **Date: 15-05-2020**

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	08-05-20	15-05-20	07	22500	380	16.89	**16.81**
	002	"	"	"	"	370	16.44	
	003	"	"	"	"	385	17.11	

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ, ಬೆಂಗಳೂರು-19

Page No. 1/1,

For Newzen Consultants Bangalore
Coordinator

Scanned with CamScanner

NC/QC/BD/2020-21/RS-CB3 Date: 18-05-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	11-05-20	18-05-20	07	22500	365	16.22	**16.15**
	002	"	"	"	"	370	16.44	
	003	"	"	"	"	355	15.78	

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬಿ.ಬಿ.ಎಂ.ಪಿ. ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ದಾಸರಹಳ್ಳಿ ವ್ಯಾಪ್ತಿಯ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ. ಬೆಂಗಳೂರು-24

For Newzen Consultants Bangalore
Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned with CamScanner

NC/QC/BD/2020-21/RS-CB4

Date: 19-05-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	12-05-20	19-05-20	07	22500	375	16.67	16.74
	002	"	"	"	"	385	17.11	
	003	"	"	"	"	370	16.44	

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ, ಬೆಂಗಳೂರು-24

For Newzen Consultants Bangalore

Page No. 1/1,

Scanned with CamScanner

NC/QC/BD/2020-21/RS-CB5

Date: 21-05-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	14-05-20	21-05-20	07	22500	380	16.89	**16.89**
	002	"	"	"	"	370	16.44	
	003	"	"	"	"	390	17.33	

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬಿ.ಬಿ.ಎಂ.ಪಿ. ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

For Newzen Consultants Bangalore
Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned with CamScanner

NC/QC/BD/2020-21/RS-CB6 Date: 22-05-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	15-05-20	22-05-20	07	22500	385	17.11	16.59
	002	''	"	''	"	370	16.44	
	003	''	"	''	"	365	16.22	

Page No. 1/1,

For Newzen Consultant Bangalore
Proprietor

Scanned with CamScanner

NC/QC/BD/2020-21/RS-CB7 **Date: 23-05-2020**

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	16-05-20	23-05-20	07	22500	370	16.44	**16.22**
	002	"	"	"	"	365	16.22	
	003	"	"	"	"	360	16.00	

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬಿ.ಬಿ.ಎಂ.ಪಿ. ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರ
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

Page No. 1/1,

For Newzen Consultants Bangalore
Director

Scanned with CamScanner

NC/QC/BD/2020-21/RS-CB1A

Date: 04-06-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	07-05-20	04-06-20	28	22500	505	22.44	**22.59**
	002	"	"	"	"	520	23.11	
	003	"	"	"	"	500	22.22	

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ, ಬೆಂಗಳೂರು-24

For Newzen Consultants Bangalore

Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned with CamScanner

NC/QC/BD/2020-21/RS-CB2A

Date: 05-06-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).

{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}

Ref.: Material testing/PMC/20-21,

Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.

Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	08-05-20	05-06-20	28	22500	515	22.89	**22.81**
	002	"	"	"	"	500	22.22	
	003	"	"	"	"	525	23.33	

Page No. 1/1,

For, Newzen Consultants Bangalore

Proprietor

Scanned with CamScanner

NC/QC/BD/2020-21/RS-CB3A

Date: 08-06-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	11-05-20	08-06-20	28	22500	510	22.67	**23.04**
	002	"	"	"	"	525	23.33	
	003	"	"	"	"	520	23.11	

For Newzen Consultants Bangalore

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned with CamScanner

NC/QC/BD/2020-21/RS-CB4A Date: 09-06-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	12-05-20	09-06-20	28	22500	515	22.89	**22.52**
	002	''	"	''	"	495	22.00	
	003	''	"	''	"	510	22.67	

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಎಂಜಿನಿಯರವರ ಕಛೇರಿ ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ ಬಿ.ಬಿ.ಎಂ.ಪಿ.

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಎಂಜಿನಿಯರವರ ಕಛೇರಿ ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ ಬಿ.ಬಿ.ಎಂ.ಪಿ. ಬೆಂಗಳೂರು-24

For Newzen Consultants Bangalore
Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned with CamScanner

NC/QC/BD/2020-21/RS-CB5A

Date: 11-06-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	14-05-20	11-06-20	28	22500	510	22.67	**22.37**
	002	"	"	"	"	495	22.00	
	003	"	"	"	"	505	22.44	

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned with CamScanner

NC/QC/BD/2020-21/RS-CB6A **Date: 12-06-2020**

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	15-05-20	12-06-20	28	22500	525	23.33	**22.96**
	002	"	"	"	"	515	22.89	
	003	"	"	"	"	510	22.67	

Page No. 1/1,

For Newzen Consultants Bangalore
Proprietor

Scanned with CamScanner

NC/QC/BD/2020-21/RS-CB7A

Date: 13-06-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Construction of RCC Drains and RCC Culverts at Right Side Cross Roads of 1st Main Road Kuvempu Nagara in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	16-05-20	13-06-20	28	22500	500	22.22	**22.44**
	002	‘’	“	‘’	“	510	22.67	
	003	‘’	“	‘’	“	505	22.44	

Page No. 1/1,

For Newzen Consultants Bangalore
Proprietor

Scanned with CamScanner